

ABSTRACT OF THE DISCLOSURE

The present invention provides a simple method for fabricating fiber-optic glass preforms having complex refractive index configurations and/or dopant
5 distributions in a radial direction with a high degree of accuracy and precision. The method teaches bundling together a plurality of glass rods of specific physical, chemical, or optical properties and wherein the rod bundle is fused in a manner that maintains the cross-sectional composition and refractive-index profiles established by the position of the rods.

5
10
15
20
25
30
35
40
45
50
55
60
65
70
75
80
85
90
95
100